



PolyIDcard™

Polycarbonate film C71-C

- ◇ Color: higher haze and semitransparent
- ◇ Thickness: 0.035mm~0.76mm
- ◇ Common thickness: 0.1mm
- ◇ Application: laser etching layer of ID cards

Product Datasheet

Item	Property	Value	Unit	Test Method
Physical	Density	1.2	g/cm ³	ISO 1183
	Haze	>75	%	ASTM D1003
	Light Transmission	>85	%	ASTM D1003
Mechanical	Tensile Strength	58	Mpa	ISO 527
	Elongation	>100	%	ISO 527
	Tensile Modulus	2250	MPa	ISO 527
Electrical	Dielectric Constant	3	-	IEC60250
	Resistant Puncture Voltage	30	KV/mm	IEC 60243
	Surface Resistivity	1.00E+15	Ω/square	IEC 60093
	Volume Resistivity	1.00E+16	Ω-cm	IEC 60093
Thermal	Coefficient of Thermal Expansion	5.8	×10 ⁻⁵ /°C	ISO 11359
	Thermal Shrinkage (at 150°C,30min)	0.5~0.7	%	ASTM D1204
	Glass Transition Temperature	152	°C	ISO 11357
	Vicat Softening Temperature	156	°C	ISO 306
Flammability	UL94	V-2/VTM-2		E249605

Tip: This test data is for reference only, not as an absolute application index



Address: No.158-30,Huashan road, SND, Suzhou, China
Tel: +86 512 66652011 Fax: +86 512 66652012
E-mail: omay@pc-film.com Web: www.pc-film.com